AMEXISAN ARSEN MANOUKIAN



TEXPRINT COLORANTI		
GIALLO 18	Full shade 40 g/Kg Reduction 1/4	
GIALLO 19	Full shade 40 g/Kg Reduction 1/4	
GIALLO 20	Full shade 30 g/Kg Reduction 1/4	
GIALLO 22	Full shade 30 g/Kg Reduction 1/7	
GIALLO 23	Full shade 30 g/Kg Reduction 1/7	
GIALLO 24	Full shade 40 g/Kg Reduction 1/7	
GIALLO 25	Full shade 30 g/Kg Reduction 1/7	
GIALLO 26	Full shade 30 g/Kg Reduction 1/7	
GIALLO 27	Full shade 30 g/Kg Reduction 1/7	
ARANCIO 31	Full shade 30 g/Kg Reduction 1/7	
ARANCIO 32	Full shade 30 g/Kg Reduction 1/7	
ARANCIO 33	Full shade 40 g/Kg Reduction 1/7	
ARANCIO 34	Full shade 30 g/Kg Reduction 1/7	
SCARLATTO 35	Full shade 40 g/Kg Reduction 1/7	
SCARLATTO 36	Full shade 40 g/Kg Reduction 1/7	
ROSSO 43	Full shade 40 g/Kg Reduction 1/7	
ROSSO 40	Full shade 40 g/Kg Reduction 1/7	
ROSSO 41	Full shade 40 g/Kg Reduction 1/7	
ROSSO 44	Full shade 40 g/Kg Reduction 1/7	
ROSSO 42 ·	Full shade 40 g/Kg Reduction 1/7	

TEXPRINT COLORANTI		
ROSSO 45	Full shade 40 g/Kg Reduction 1/7	
ROSSO 46	Full shade 40 g/Kg Reduction 1/7	
ROSSO 49	Full shade 40 g/Kg Reduction 1/7	
ROSSO 48	Full shade 40 g/Kg Reduction 1/7	
RUBINO 47	Full shade 40 g/Kg Reduction 1/7	
RUBINO 37	Full shade 40 g/Kg Reduction 1/7	
BORDEAUX 38	Full shade 40 g/Kg Reduction 1/7	
ROSSO VIOLETTO 39	Full shade 40 g/Kg Reduction 1/7	
VIOLA 50	Full shade 40 g/Kg Reduction 1/7	
VIOLA 51	Full shade 20 g/Kg Reduction 1/7	
BLU 55	Full shade 40 g/Kg Reduction 1/7	
BLU 56	Full shade 40 g/Kg Reduction 1/7	
BLU 52	Full shade 40 g/Kg Reduction 1/7	
BLU 54	Full shade 80 g/Kg Reduction 1/4	
BLU 57	Full shade 30 g/Kg Reduction 1/7	
BLU 53	Full shade 30 g/Kg	
BLU 58	Full shade 30 g/Kg Reduction 1/7	
BLU 59	Full shade 30 g/Kg Reduction 1/7	
TURCHESE 15	Full shade 30 g/Kg Reduction 1/7	
TURCHESE 16	Full shade 30 g/Kg Reduction 1/7	

TEXPRINT COLORANTI		
VERDE 60	Full shade 30 g/Kg Reduction 1/7	
VERDE 61	Full shade 30 g/Kg Reduction 1/7	
VERDE 62	Full shade 30 g/Kg Reduction 1/7	////
VERDE 63	Full shade 30 g/Kg Reduction 1/7	
VERDE 64	Full shade 30 g/Kg Reduction 1/7	
BRUNO 70	Full shade 30 g/Kg Reduction 1/7	
BRUNO 71	Full shade 30 g/Kg Reduction 1/7	
BRUNO 72	Full shade 30 g/Kg Reduction 1/7	
BRUNO 73	Full shade 30 g/Kg Reduction 1/7	
BRUNO 74	Full shade 30 g/Kg Reduction 1/7	
BRUNO 75	Full shade 30 g/Kg Reduction 1/7	
BRUNO 76	Full shade 30 g/Kg Reduction 1/7	
BRUNO 77	Full shade 30 g/Kg Reduction 1/7	
BRUNO 78	Full shade 30 g/Kg Reduction 1/7	
GRIGIO 79	Full shade 30 g/Kg Reduction 1/15	
NERO 85	Full shade 60 g/Kg Reduction 1/20	
NERO 82	Full shade 60 g/Kg Reduction 1/20	
NERO 83	Full shade 60 g/Kg Reduction 1/20	
NERO 84	Full shade 60 g/Kg Reduction 1/20	
NERO 80	Full shade 60 g/Kg Reduction 1/20	
NERO 81	Full shade 60 g/Kg Reduction 1/20	

S - COLORI FLUORESCENTI	
Full shade 60 g/Kg	
Full shade 100 g/Kg	
Full shade 60 g/Kg	
	Full shade 60 g/Kg Full shade 60 g/Kg Full shade 60 g/Kg Full shade 60 g/Kg Full shade 100 g/Kg


Colours showed in the shade card are merely indicative I colori rappresentati nella cartella sono solamente indicativi

"Storage and ending"

Texprint coloranti pigments are stable on storage for one year but performance may be affected by climatic extremes, such as freezing. Ensure partially used drums are kept properly sealed. Mixing is always recommended prior to use.

Water based pigments

Fastness - Solidi	ità			Dry clea	oning				
rastiless - Solidi	lua.	Artificia		Lavaggio					
		Luce art Xeno		Perchloroe Percloro		Chlorine Cloro	PVC coating Plastificazione con PVC	Discharge Corrosione	
Texprint coloranti		Full shade F		Full shade f		Full shade	Full shade	Full shade	Note
	***	7	6	5	5	5	5	5	
GIALLO 18 GIALLO 19		7	6-7	2	2	5	1	5	* turns shade with
GIALLO 20		7	5-6	4-5	3-4	5	4	5	chlorine
GIALLO 22		6	4-5	3-4	2-3	5	3-4	5	vira al cloro
GIALLO 23	***	6	4-5	4	2-3	5	3-4	5	**
GIALLO 24	***	7-8	7-8	5	5	5	5	1	not fast to acids, nor
GIALLO 25	*/***	7	6-7	5	5	4	5	5	to gas-fading non resiste agli acidi
GIALLO 26		6	5	4	4	5	2-3	5	e al gas-fading
GIALLO 27	***	5-6	4-5	3	2	5	2	5	rannang palajaga
ARANCIO 31		5-6	4-5	4	3-4	5	2	5 5	***
ARANCIO 32		6-7	5-6	4-5	4	5 5	2	5	selected for the best resistance to heat
ARANCIO 33		6-7	6-7	2	3-4	5	2	5	selezionati per la
ARANCIO 34		6-7	5	4-5 5	5	5	4	1	migliore resistenza al calore
SCARLATTO 35	NO. 12. 12. 12. 12. 12. 12. 12. 12. 12. 12	6-7	5 5-6	4-5	4-5	4-5	3	1	No.
SCARLATTO 36		7-8	7	2	2	5	1	1	a guarante de la constanta de
ROSSO 43	***	7-8	7	5	5	5	5	5	Дринизальна
ROSSO 40 ROSSO 41		5-6	4-5	2	2	5	1	1	
ROSSO 44		7	6-7	5	5	5	4	2-3	generativeng
ROSSO 42		6-7	6-7	5	5	5	3-4	4-5	
ROSSO 45	***	6	5	5	5	5	5	5	generative
ROSSO 46	***	6	5	5	5	5	3	4	
ROSSO 49	*	5-6	4-5	4	4	4	2-3	4	en-series de la company de la
ROSSO 48		6-7	6	5	5	5	3	2-3	
RUBINO 47		7	6-7	5	4-5	2	5	5	na-a-a-a-ggingi
RUBINO 37		6	5-6	4	3	5	1	1	
BORDEAUX 38		6-7	6	2	1	5	1	1 4	
ROSSO VIOLETTO 39		5-6	4	4-5	4	4	1-2	5	
VIOLA 50	*	7	7	5	5	4-5* 4-5	5	5	
VIOLA 51	*	7	6-7	5	5 4-5	5	3-4	2	one control of the co
BLU 55	*/***	6-7	7	4-5 4-5	4-5	4-5	4-5	5	The state of the s
BLU 56		8	7-8	4-5	4-5	5	5	5	
BLU 52	**	7-8	6-7	4-5	4-5	5	5	5	
BLU 54 BLU 57	***	7-8	7	4-5	4-5	5	4-5	5	National Control of the Control of t
BLU 53	***	7-8	7	4-5	4-5	5	4-5	5	
BLU 58	***	7-8	7	4-5	4-5	5	5	5	The second secon
BLU 59		7-8	7	5	5	5	5	5	
TURCHESE 15		7-8	- 7	5	5	5	5	. 5	
TURCHESE 16		7-8	7	4-5	4-5	5	5	5	
VERDE 60		6-7	6	4-5	4	5	3	5	
VERDE 61		6-7	6	4-5	4	5	3	5	
VERDE 62		7-8	7	5	5	5	5	5	The state of the s
VERDE 63	**	7-8	7	5	5	5	5	5 2	
VERDE 64	**	6-7	5-6	4-5	4	5	3	1	
BRUNO 70		7-8	7	5 1-2	5 1-2	4-5 4-5	2-3	3	
BRUNO 71	*	6-7 6	5-6 5	5	4-5	4	2-3	2	
BRUNO 72 BRUNO 73		5-6	4-5	2	2	4	1	2	regularization of the control of the
BRUNO 74		6	5	4-5	4-5	4-5	3-4	3	and the state of t
BRUNO 75		5-6	4-5	2	2	5	1	1	enemana de la companya de la company
BRUNO 76		6-7	6	5	4	5	4	. 1	
BRUNO 77	***************************************	7	6-7	5	5	5	4-5	4-5	- incommon
BRUNO 78		7-8	7-8	4-5	4-5	5	4	4-5	
GRIGIO 79	***	7	6-7	5	4	5	5	4	Винестина
NERO 85	***	7-8	7	5	5	5	5	1	
NERO 82	***	7-8	7	5	5	5	5	1	
NERO 83	***	7-8	7	5	5	5	5	1	
NERO 84	***	7-8	7	5	5	5	5	1	The state of the s



Viale dello Sport, 12 22070 Appiano Gentile Como - Italy Tel. +39 031 931923 Fax +39 031 933789 info@amexsrl.it www.amexsrl.com